

Negative Longitudinal Magnetoresistance and Angle Dependent Transport Near the Quantum Limit in Cd_3As_2 Films

I. A. Leahy¹⁺, A. D. Rice¹, H. Ness², J. N. Nelson¹, M. van Schilfgaarde¹, and K. Alberi^{1,3}

¹National Laboratory of the Rockies, Golden, Colorado 80401, USA

²Department of Physics, King's College London, Strand, London WC2R 2LS, UK

³Renewable and Sustainable Energy Institute, National Renewable Energy Laboratory and University of Colorado, Boulder, 80301, CO, United States

The field angle dependence of magnetoresistance (MR) in topological semimetals can contain information about mobility anisotropy and topological transport [1-4]. Here, we report on angle dependent magnetotransport in (001)-oriented Cd_3As_2 thin films with ultralow carrier densities ($\sim 2 \cdot 10^{16} \text{ cm}^{-3}$) near their quantum limit. With increasing field magnitude, we identify a striking crossover in the $H \parallel I$ transport from negative longitudinal MR to a huge positive longitudinal MR with magnitude comparable to the transverse MR (Figure 1). Using systematic transport measurements and theoretical




Figure 1: 2 K, fractional MR ($FMR = \frac{\rho_{xx} - \rho_0}{\rho_0} \cdot 100\%$) for an (001) Cd_3As_2 film exhibiting the crossover from negative to positive longitudinal MR with increasing field magnitude.

modeling of the transport with an $8 \times 8 \mathbf{k} \cdot \mathbf{p}$ model, we identify a unique quantum-limit contribution governed by Fermi surface anisotropy. We discuss these results within the context of previously undescribed field-angle dependent quantum limit transport in other semimetals.

References:

- ¹ I. A. Leahy, A. D. Rice, J. N. Nelson, H. Ness, M. van Schilfgaarde, D. Graf, A. Suslov, W. Pan, and K. Alberi, *Interplay of Quasi-Quantum Hall Effect and Coulomb Disorder in Semimetals*, [Nature Communications Materials](#) (2026).
- ² A. Collaudin, B. Fauque, Y. Fuscya, W. Kang, and K. Behnia, *Angle Dependence of the Orbital MR in Bismuth*, [Physical Review X](#), **5**, 021022 (2015).
- ³ J. Wang, H. Yang, L. Ding, W. You, C. Xi, J. Cheng, Z. Shi, C. Cao, Y. Luo, Z. Zhu, J. Dai, M. Tian, and Y. Li, *Angle-dependent MR and its implications for Lifshitz transition in W_2As_3* , [npj quantum materials](#), **4**, 58 (2019).
- ⁴ S. Ghosh, A. Low, N. Devaraj, S. Changdar, A. Narayan, S. Thirupathaiah, *Extremely large and angle dependent MR in Kagome Dirac Semimetal RFe_6Sn_6 ($R = \text{Ho, Dy}$)*, [Journal of Alloys and Compounds](#), **1040** 183506 (2025).

⁺ Author for correspondence: Ian.Leahy@nlr.gov